

## Nye Uniflor 4622 R

**A Severe Service, Non-Oxidizing Lubricant  
for Bearings and Mechanical Devices  
Where Good Film Strength Is Needed at  
High Temperatures and/or Fuel or  
Chemical Resistance Is Required**

### Typical Properties :

Characteristics	Test Methods	Unit	Specifications
Colour	Visual	–	White
Appearance	Visual	–	Smooth
Thickener	–	–	PTFE
Base Oil - Synthetic [PFPE]		–	PFPE
Viscosity @ 100°C	ASTM D-445	cSt	47
@ 40°C	ASTM D-445	cSt	510
Viscosity Index	ASTM D-2270	–	135
Flash Point	ASTM D-92	°C	None (non-flammable)
Pour Point	ASTM D-97	°C	- 20
Penetration Unworked	ASTM D-217	0.1 mm	254
Penetration Worked [60 X]	ASTN D-217	0.1 mm	272
NLGI Grade		–	# 2
Density @ 25°C	ASTM D-1480	gm / cc	1.94
Dropping Point	ASTM D-2265	°C	Non-Melting
Oil Separation [24 hrs] @ 100°C	FTM 791B, 321.2	%	0.1
@ 150°C	FTM 791B, 321.2	%	4.9
Evaporation [24 hrs] 150°C	ASTM D-972	%	0
Water Washout [60 mins.] 80°C, wt. loss	ASTM D-1264	%	1.1
Copper Corrosion [24 hours] @ 150°C	ASTM D-4048	–	2a, No Corrosion
Four Ball Wear 60 min., 1200 RPM @ 75°C 40 kg.load	ASTM D-2266	mm	0.66
Oxidation Stability [168 hours] @ 100°C	ASTM D-942	psig	0.5
Bearing Rust Test [24 hours] 52°C	ASTM D-1743	–	Pass (No Corrosion)
Recommended Service Temp. Range	–	°C	- 20 to 250

Make : Nye Lubricants, Inc. U.S.A.

MSDS available on request.

Due to continual upgradation of products above data is subject to change without notice  
This supersedes our previously issued data sheets.

[REV.4 / 01.01.14]

Information and data given herein is offered in good faith as accurate, but without guarantee. Conditions of use and suitability of a product for a particular use is beyond our control; all risks of use of the product are therefore assumed by the user and WE EXPRESSLY DISCLAIM ALL WARRANTIES OF EVERY KIND AND NATURE.

**Anand Engineers Pvt Ltd.** 66, MIDC, Road No. 13, Andheri (East), Mumbai - 400093, INDIA.

Tel :+91 22 28219292/8/9 Fax: +91 22 28379337 Email: sales@molygraph.com Web: www.molygraph.com